



TECHNICAL DATA OF MEMBRANCE RV-Memb-850

Feature:

- 1.Safe and Durable.
- 2.High tensile, tear and adhesion strength.
- 3.Excellent ability on Waterproof, anti-UV, fire retardant, mouldproofing, antiabrasion and self-cleaning.
- 4.Good resilience, Outstanding opacity.
- 5.Ideal for membrane,high-ends projects, mega marquees, or mobile constructions at harsh conditions.

Specification:

Base fabric	1000Dx1000D 20x20/sq.yd 1100dtex x1100dtex 8x8/sq.cm	DIN 53830/DIN60001 ASTM D 751
Weight	850gsm+/- 20gsm	DIN53352
Lacquering	25oz	ASTM D 751
Breaking strength (Warp/weft)	2740/2435 N/5cm 623lbs/553lbs/2"	DIN 53354 FS 5100
Tearing strength	430/325 N/5cm 98lbs/74lbs	DIN 53363 FS 5100
Adhesion strength	105N/5cm 24lbs/2"	DIN 53357 FS 5970
Avilable width	1000-3200mm 36"-126"	
Fire retardant	M2, B1, NFPA 701, B2	
Temperature resistance	- 30°C ~ 70°C - 20°F ~ 158°F	DIN 53372 FS 5874

NOTE: All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty.



HANGZHOU REEVOO INDUSTRY CO., LTD.

Add.:No.159-4 Fengpu Road, Fuyang District,

Hangzhou, Zhejiang, China. P.C.:311400

Tel:+86-571-23281868 Fax:+86-571-23281899

Email:reevoo@reevoo.net.cn

Http://www.reevooindustrial.com